

TROJAN° DATA SHEETMOTIVE T1275-AGM Pro

MODEL	T1275-AGM Pro
VOLTAGE	12
CAPACITY	133Ah @ 20Hr
MATERIAL	Polypropylene
BATTERY	VRLA AGM / Non-Spillable / Maintenance-Free
COLOR	Maroon
WATERING	No Watering Required



12 VOLT

PHYSICAL SPECIFICATIONS

BCI	MODEL NAME	TERMINAL TYPE ^G	DIMENSIONS ° INCHES (mm)			WEIGHT ' LBS. (kg)	HANDLES	INSTALLATION ORIENTATION
			LENGTH	WIDTH	HEIGHT ^F			Horizontal and Vertical
GC12	T1275-AGM Pro	M8/AP/LT	13.03 (331)	7.08 (180)	10.96 (278)	94.14 (42.7)	Embedded	

ELECTRICAL SPECIFICATIONS

VOLTAGE	Cranking P	erformance	Capacity	^A Minutes	CAPACITY ^B AMP-HOURS (Ah)		ENERGY (kWh)	INTERNAL RESISTANCE (m Ω)	SHORT CIRCUIT CURRENT (amps)		
10	C.C.A. ^D @0°F	C.A. ^E @32°F	@ 25 Amps	@ 75 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr	2.00	2920
12	-	-	255	69	114	126	133	135	1.62	3.29	2920

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)				
12V	24V	36V	48V	
20% of C ₂₀				
14.40	28.80	43.20	57.60	
13.50	27.00	40.50	54.00	
	12V 14.40	12∨ 24∨ 20% 14.40 28.80	12V 24V 36V 20% of C20 20% 43.20	

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

ADD	SUBTRACT				
0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F	0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F				
OPERATIONAL DATA					


OPERATING TEMPERATURE	SELF DISCHARGE
-4°F to 122°F (-20°C to 50°C) At temperatures below 32°F (0°C) maintain a state of charge greater than 60%	Less than 3% per month depending on storage temperature conditions

RECYCLE RESPONSIBLY





STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE

PERCENTAGE CHARGE	CELL	12 VOLT
100	2.14	12.84
75	2.09	12.54
50	2.04	12.24
25	1.99	11.94
0	1.94	11.64




BATTERY DIMENSIONS (shown with M8)





TERMINAL CONFIGURATIONS⁶



F

10.96 (278)

10.57 (268)

A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are

The function of initiation of the set of the В


С

C.C.A. (Cold Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell. D




MASTER DISTRIBUTOR

Designed in compliance with applicable BCI, DIN, BS and GB/T standards. Tested in compliance to BCI and GB/T standards.



SELF DISCHARGE VS. TIME[#]



E. C.A. (Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F (0°C) at a voltage above 1.2 Vicel This is sometimes referred to a main crant and the second and the second and the second at 22 Well. This is sometimes referred to a main crant and any angle 322 F. Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal. Terminal images are representative only.

G.

A boost charge should be performed every 6 months when batteries are in storage. H. Weight may vary.

> 1300 737 244 supercharge.com.au